



# Tin-Lead Solder Paste

## SH-6388WA

Rev. 2017/09/17 Ver. 01-01

### BASIC OVERVIEW



Sn63Pb37 Alloy  
Tin-Lead Solder Paste  
Water Soluble

### APPLICATIONS

Water Soluble Tin-Lead SMD Solder Paste  
Wide Range of Applications and PCB designs

### FEATURES

Appearance	Gray paste w/o visible foreign and clusters	
Alloy Composition	Sn63/Pb37	JIS-Z-3282
Melting Point	183 °C	
Particle Size	(Type 3) +45µm < 1% , - 20µm < 10% (Type 4) +38µm < 1% , - 20µm < 10%	J-STD-005
Powder Shape	Spherical	
Flux Content	11.0 ± 1.0 wt%	JIS-Z-3197, 8.1.2
Viscosity	200 ± 50 Pa.s (25±1°C, 10rpm, Malcom)	JIS-Z-3284 Annex 6
Flux Type	ORM1	J-STD-004

### Alloy Detail Composition

(Sn)	(Pb)	(Sb)	(Bi)	(Cd)	(Cu)	(Au)	(In)	(Ag)	(Al)	(As)	(Fe)	(Ni)	(Zn)
62.5~ 63.5	REM.	0.05 MAX	0.10 MAX	0.002 MAX	0.05 MAX	0.05 MAX	0.10 MAX	0.10 MAX	0.001 MAX	0.03 MAX	0.02 MAX	0.01 MAX	0.001 MAX

(wt%)

Scan Code for Solder  
Paste Documents





# Tin-Lead Solder Paste

## SH-6388WA

Rev. 2017/09/17 Ver. 01-01


### PERFORMANCE & RELIABILITY

Copper Plate Corrosion Test	Pass	IPC-TM-650, 2.6.15
Halogen Content Test	<2.0%	JIS-Z-3197, 8.1.4.2.1
Spreading Test	> 90%	JIS-Z-3197, 8.3.1.1
Copper Mirror Test	Pass	IPC-TM-650, 2.3.32
Viscosity Test (25°C, 10 rpm)	200 ± 50 Pa.s	JIS-Z-3284. Annex 6
Tackiness Test (gf)	> 120 (8hr)	JIS-Z-3284. Annex 9
Slump Test	Less than 0.3mm	JIS-Z-3284. Annex 7,8
Solder Ball Test	Pass	JIS-Z-3284. Annex 11

S.I.R. Test	▲ > 1 x 10 <sup>9</sup> Ω, Pass	IPC-TM-650, 2.6.3.3
Electro Migration Test	◆ Pass	IPC-TM-650, 2.6.14.1

▲ Test Conditions : 85 °C, 85% RH for 168hrs    ◆ Test Conditions: 65°C, 88.5% RH for 596 hrs

### RECOMMENDED REFLOW PROFILE



Ramp Up Rate (30-120°C):	1.0-3.0 °C/sec
Pre-heating Time (120-170°C):	60-120 sec
Time Period Above 183°C:	30-60 sec
Ramp Up During Reflow:	1.0-3.0 °C/sec
Peak Temperature:	210-230 °C
Ramp Down Cooling Rate:	1.0-3.0 °C/sec

Note: The recommended reflow profile is provided as a guideline. Optimal profile may differ due to oven type, assembly layout or other process variables.



# Tin-Lead Solder Paste

## SH-6388WA

Rev. 2017/09/17 Ver. 01-01

### STORAGE & HANDLING:

- Refrigerate the solder paste at 0-10°C. Shelf life is 6 months from production date.
- Allow the paste to reach defined printing temperature (room temperature) for 3-4 hrs. Do not heat up the solder paste rapidly.
- For jars packaging, mix the solder paste before use for 1-3 mins by plastic spatula.
- It is recommended to finish fresh paste within 24 hrs. Do not store used paste and fresh paste in the same jar.
- If printing process was interrupted for more than 1 hour, remove remaining paste from stencil and seal in the jar.
- Recommended printing environment is 22-28°C and RH 30-60% .
- Flux residue is easily cleaned by 60±5°C D.I. water with minimum pressure of 60psi, and suggested to be done within 24hrs.

*Note: For more information, please refer to solder paste application guideline sheet*

### HOW TO ORDER

## SH-6388WA – T3 – 500

Solder Alloy	Flux	Particle Size	Weight / Packaging
SH-6388 = Sn63/Pb37	WA = Water Soluble	T3 = 20-45µm T4 = 20-38µm	30 = syringe 30g 100 = syringe 100g 150 = syringe 150g 250 = plastic jar 250g 500 = plastic jar 500g 600 = small cartridge 600g 1200 = large cartridge 1200g



### CONTACTS

Tel.: +49-152-5106-5427



[support@nevo-solder.com](mailto:support@nevo-solder.com)



[www.nevo-solder.com](http://www.nevo-solder.com)

**NOTICE:** Specifications are subject to change without notice. Contact NeVo® for the latest specifications. All statements, information and data given herein are believed to be accurate and reliable, but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our product are made without responsibility or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures are indicated or that measures may not be required. Specifications are typical and may not apply to all applications.

NeVo®, Škrobářenská 506/2, 617 00 BRNO, CZECH REPUBLIC